

## ABOUT CLEARALL-DAY™

Clearlab's innovative engineers, scientists and clinical experts have successfully combined the ocular benefits of a biocompatible material – ClearGMA™- with the clinical simplicity of a unique aspheric disposable lens – Clearall-day™. Clearall-day™ is suitable for frequent replacement. The biocompatibility of ClearGMA™ is achieved through synthesising the compatibility properties of mucin, the body's natural wetting substance.


ClearGMA™ has water binding properties that enhance resistance to dehydration and increase lens surface wettability providing a greater affinity for water than ordinary contact lens materials. Wearers benefit from longer, more comfortable wearing times providing them with a truly comfortable all day lens.

## ENHANCING OCULAR PERFORMANCE

Proclear Compatibles® is the current bench-mark contact lens for biocompatibility. Clearlab®'s scientists and engineers were set the challenge of designing a contact lens that was superior to the overall benefits of Proclear Compatibles® through its material, enhanced vision, and ease of handling. The result is Clearall-day™ - the unique aspheric biocompatible frequent replacement lens from Clearlab®.

## ENHANCED VISION - ASPHERIC OPTICS

The biocompatible Clearall-day™ lens has been enhanced with aberration correcting aspheric optics to optimize the overall wearing experience. The optics incorporate innovative wavefront design and technology on the front surface of the lens.



Visual acuity is optimized over the power range and the optical design is tailored to provide maximum contrast sensitivity particularly in low illumination where it is needed most.

Patients who normally require low amounts of toric correction can benefit from Clearall-day™ lenses as the aspheric optical design can successfully mask low levels of astigmatism. The combination of aberration correcting aspheric optics and longer wetting and wearing times confirms Clearall-day™ as a truly unique lens.

## SPECIFICATIONS - Clearall-day™

<b>Material</b>	43% hioxifilcon A, 57% water
<b>Base Curve</b>	8.6 mm
<b>Diameter</b>	14.2 mm
<b>Handling Tint</b>	Light Blue
<b>Lens Design</b>	Bi-curve back surface with unique tangential flat peripheral band. Tri-curve, reducing optic anterior surface. Advanced aspheric optic design to reduce aberration. All junctions smoothed with blend curves.
<b>Power Range</b>	up to -8.00 0.00 to -6.00 (0.25D steps) -6.50 to -8.00 (0.50D steps)
<b>Nominal Edge Thickness*</b>	0.07mm
<b>Nominal Centre Thickness*</b>	0.08mm
<b>Dk @ 35°C</b>	19.85 X 10 <sup>-11</sup> (cm <sup>2</sup> /s)(mlO <sub>2</sub> /ml.mm Hg)
<b>Refractive Index at 25°C</b>	1.4050 (hydrated)
<b>Light Transmittance</b>	>95% with handling tint over the visible spectrum
<b>Specific Gravity</b>	1.08 (hydrated)
<b>Lens Care Indications</b>	Peroxide or chemical lenscare, including MPS
<b>Pack Size</b>	6 lenses
<b>Regulatory</b>	CE marked

\*-3.00 D lens